

414 Rec'd PCT/PTO 29 APR 1999

FORM PTO-1390
(REV. 5-93)U.S. DEPARTMENT OF COMMERCE
PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

3404/OF546-USO

**TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)**

09/297399

INTERNATIONAL APPLICATION NO.

INTERNATIONAL FILING DATE

PRIORITY DATE CLAIMED

PCT/JP97/04480

08 December 1997

09 December 1996

TITLE OF INVENTION

WATER BASED INK COMPOSITION FOR BALLPOINT PEN

APPLICANT(S) FOR DO/EO/US

Masaru MIYAMOTO

Applicant herewith submits to the United States Designated/Elected office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☐ This express request to begin national examination procedures (35 U.S.C. 371 (f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371 (b) and PCT Articles 22 and 39 (1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☒ has been transmitted by the International Bureau
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US)
6. ☒ A translation of the International Application into English (35 U.S.C. 371 (c)(2)).
7. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☐ have not been made and will not be made.
8. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c) (3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)) (executed).
10. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).

Items 11. to 16. below concern other document(s) or information included:

11. ☒ An Information Disclosure Statement under 37 CFR 1.79 and 1.98 (with 3 JP abstracts)
12. ☒ An assignment document for recording. A **separate** cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A FIRST preliminary amendment.
 - ☐ A SECOND or SUBSEQUENT preliminary amendment.
14. ☐ A substitute specification.
15. ☐ A change of power of attorney an/or address letter.
16. ☒ Other items or information: AFFIRMATION OF PRIORITY CLAIM

EXPRESS MAIL CERTIFICATE

Date: 4-29-99 Filed No: EN 445423844
 I hereby certify that, on the date indicated above I
 deposited this paper or fee with the U.S. Postal Service
 & that it was addressed for delivery to the Commissioner
 of Patents & Trademarks, Washington D.C. 20231 by
 "Express Mail Post Office to Addressee" service.

Name (Print)

G. KARASZI G. Karaszi

Signature

U.S. APPLICATION NO. (if known sec 37 C.F.R.1.50

INTERNATIONAL APPLICATION NO.:

Attorney's Docket Nu

PCT/JP97/04480

3404/0F546-USO

17. [X] The following fees are submitted:

Basic National Fee (37 CFR 1.492 (a)(1)-(5)):Search Report has been prepared by the EPO ___ or JPO X \$840.00

International preliminary examination fee paid to USPTO (37 CFR 1.482) ___ \$670.00

No international preliminary examination fee paid to USPTO (37 CFR 1.482)
but international search fee paid to USPTO (37 CFR 1.445 (a) (2))... \$760.00

Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO..... \$970.00

International preliminary examination fee paid to USPTO (37 CFR 1.482)
and all claims satisfied provisions of PCT Article 33(2)-(4)..... \$96.00

ENTER APPROPRIATE BASIC FEE AMOUNT =

\$840.00

Surcharge of \$130.00 for furnishing the oath or declaration later than []20 []30
months from the earliest claimed priority date (37 CFR 1.492(e)).

\$

Claims	Number Filed	Number Extra	Rate		
Total Claims	3-20 =	0	X \$22.00	\$	
Independent Claims	1-3 =	0	X \$80.00	\$	
Multiple dependent claims(s) (if applicable)			+ 270	\$	

TOTAL OF ABOVE CALCULATIONS = \$840.00

Reduction by 1/2 for filing by small entity, if applicable. Verified Small Entity statement must also be filed. (Note
37 CFR 1.9, 1.27, 1.28).

\$0.00

SUBTOTAL = \$840.00

Processing fee of \$130.00 for furnishing the English translation later the [] 20 [] 39
months from the earliest claimed priority date (37 CFR 1.492(f)).

+

TOTAL NATIONAL FEE = \$840.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). the assignment must be accompanied by an
appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property

\$40.00

TOTAL FEES ENCLOSED = \$880.00

Amount to be
refunded: \$

charged: \$

a. [X] A check in the amount of \$880.00 to cover the above fees is enclosed.

b. [] Please charge my Deposit Account No.04-0100 in the amount of \$_____ to cover the above fees.

c. [X] The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit
Account No. 04-0100. A duplicate copy of this sheet is enclosed.NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed
and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

Martin E. Goldstein

SIGNATURE



Darby & Darby P.C.

NAME Martin E. Goldstein

805 Third Avenue

REGISTRATION NO. 20,869

New York, New York 10022-7513

09/297399

29 APR 1999

EXPRESS MAIL CERTIFICATE

DATE 4-29-99 LABEL NO. EM 445423844

I HEREBY CERTIFY THAT, ON THE DATE INDICATED ABOVE I
DEPOSITED THIS PAPER OR FILE WITH THE U.S. POSTAL SERVICE
& THAT IT WAS ADDRESSED FOR DELIVERY TO THE COMMISSIONER
OF PATENTS & TRADEMARKS, WASHINGTON, DC 20231 BY "EXPRESS
MAIL POST OFFICE TO ADDRESSEE" SERVICE.

NAME (PRINT)

SIGNATURE

G Karasz

3404/0F546-US0

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of: Masaru MIYAMOTO

Filed: Concurrently
(U.S. National Phase of
International Application No. PCT/JP97/04480
International Filing Date: 08 December 1997)

For: WATER BASED INK COMPOSITION FOR BALLPOINT PEN

PRELIMINARY AMENDMENT

Hon. Commissioner of
Patents and Trademarks
Box PCT
Washington, DC 20231

ATTN: DO/EO/US

Sir:

Prior to examination, please amend the above-identified
patent application as follows:

In the Claims:


Page 10, line 6, delete "alkali-swelling associative thickeners" and substitute therefor -- alkali-swelling thickeners --.

R E M A R K S

The specification has been amended to correct a minor translation error.

Entry of this amendment is respectfully requested.

Respectfully submitted,


Martin E. Goldstein
Reg. No. 20,869
Attorney for Applicant(s)

MEG:wo

DARBY & DARBY P.C.
805 Third Avenue, 27th Flr.
New York, NY 10022
212-527-7700

M:13404\0F546\W00889

DESCRIPTION

WATER BASED INK COMPOSITION FOR BALLPOINT PEN

5

Technical Field

The present invention relates to a water based pigment ink composition for a ballpoint pen, more specifically to a water based pigment ink composition used for a free ink type ballpoint pen having structure in which an ink is stored directly in an ink reservoir having a small diameter without using an ink absorber and a feed to be fed to a pen tip.

15

Background Art

In general, an ink for a ballpoint pen includes a water based ink of a low viscosity containing a solvent comprising water and a water soluble solvent and having an ink viscosity of 10 mPa·s or less and an oil based ink containing a solvent such as a polyhydric alcohol and Cellosolve and having an ink viscosity of 1000 to 20000 mPa·s.

20

25

A ballpoint pen using an oil based ink has structure in which the ink adhered on a ball at a pen tip through an ink reservoir having a small diameter is transferred on a paper surface by rotation of the ball

and only the transferred portion of the ink is fed to the pen tip through the reservoir.

A ballpoint pen using a water based ink has structure in which an ink is fed to a ball surface and a paper surface by means of capillary action of a feed prepared by binding fine fibers.

The foregoing water based ink and oil based ink for a ballpoint pen each have excellent advantages. On the other hand, however, they have various problems as well.

For example, since the water based ink has a low viscosity, the ink is fed by making use of a principle of capillary action. When the point portion of the ballpoint pen simply contacts paper, the capillary action is exerted on the contact point to feed the ink, and good lines can be written on a paper surface without applying so much writing pressure, so that splitting, starving and blobbing scarcely take place. On the other hand, the capillary action is exerted as well after transferring the ink on a paper surface to cause the drawn lines to feather, and storing the ink directly in the ink reservoir allows the ink to seep due to vibration or impact to make the amount of the ink to be fed to the ball unstable. Accordingly, complicated structure having a feed prepared by binding fine fibers is required. Further, there is a problem that it is difficult to

confirm the amount of the ink reserved in the ballpoint pen.

On the other hand, the oil based ink is characterized by that because of a high viscosity thereof, the ink can be stored directly in the ink reservoir having a small diameter and the structure of the ballpoint pen can be simplified and that the remaining amount of the ink can be confirmed by using a transparent material for the ink reservoir and the ink transferred on a paper surface does not feather. On the other hand, there are problems that since the ink is transferred only on a paper surface contacted with the rotating ball, splitting and starving are liable to be caused if the ball rotates unstably and that since the ink hardly penetrates into a paper surface, blobbing which causes stain with the untransferred ink is apt to be caused.

In recent years, several countermeasures for solving such problems are reported. For example, the problems of feathering and seepage of an ink have been investigated in Japanese Patent Application Laid-Open No. Sho 54-98826 to provide a water based ink for a ballpoint pen in which gelatinizers (benzyl sorbitol and benzylidene xylitol or derivatives thereof) or a water soluble paste is added to provide the ink with thixotropy. Further, provided are a water based ink for a ballpoint

pen in which the viscosity is increased by a cross linking type acrylic resin in Japanese Patent Application Laid-Open No. Sho 57-49678 and a water based ink for a ballpoint pen in which the viscosity is increased by xanthane gum in U.S. Patent 4545818. However, they have problems of splitting and of stain caused by blobbing, and therefore they are not sufficiently satisfactory.

Further, it is shown in U.S. Patent 4671691 to store a water based ink in a barrel of a simplified free ink type pen such as an oil based ballpoint pen, and disclosed therein is a ballpoint pen comprising a water based ink in which a water dispersible rubber or resin is added to provide a shear thinning property and a thinning index thereof falls in a range of from 0.01 to 0.6, and a viscoelastic follower. However, there are the defects that an ink subjected to shearing is not good in a flowing property and is slow in temporal viscosity recovery, so that a follow-up property of the ink in writing is inferior to bring about starving of the drawn lines and the ink seeps immediately after writing, and therefore the ballpoint pen is not sufficiently satisfactory.

Further, shown in Japanese Patent Application Laid-Open No. Hei 6-346014 is a water based ink for a ballpoint pen provided with thixotropy by a thickener

comprising an emulsion to be thickened in alkaline. However, there are the problems that a settling action of a pigment can not be prevented only by an increase in the viscosity only with a swelling action of a carboxyl group contained in the thickener, so that the ink in the circumference of a rotary ball at the pen tip seeps and that the ink does not have a long term storing property. Accordingly, it is not sufficiently satisfactory.

An object of the present invention is to solve the problems on the conventional technologies described above and provide a water based ink composition which has a good follow-up property in writing and solves conventional defects such as splitting, poor water resistance and stain of drawn lines caused by blobbing and which does not cause seepage in the circumference of the rotary ball immediately after writing and is stable over a long period of time without settling of a pigment itself, wherein the water based ink composition can be filled in a ballpoint pen having structure in which an ink is stored directly in an ink reservoir to be fed to a pen tip, that is, a ballpoint pen having simplified free ink type structure as is the case with a ballpoint pen for a so-called oil based ink.

The present inventors have made researches in order to solve the problems described above, and as a result, they have come to complete a water based ink in which dispersibility of a pigment is kept stable over an extended period of time and a follow-up property of the ink in writing and quality of the drawn lines are excellent and which does not bring about seepage in the circumference of the rotary ball and can be stored in a ballpoint pen having simplified free ink type structure by using a thickener having a hydrophobic group and a hydrophilic group in a molecule which increases a viscosity by a steric hindrance resistance viscosity brought about by hydration swelling of the hydrophilic group in the thickener molecule and associative adsorption of the hydrophobic group and the hydrophilic group in the thickener molecule on the components contained in the ink composition instead of exerting a single thickening action brought about only by a steric hindrance resistance of the thickener molecule.

The water based ink composition of the present invention for a ballpoint pen is composed of an alkali-swelling associative thickener comprising a polymer having a carboxyl group as a hydrophilic group and a hydrophobic group, a pigment, a polar solvent containing water, a pH controlling agent and other additives.

Preferred is the water based ink composition for a ballpoint pen in which the alkali-swelling associative thickener described above is contained in a proportion of 0.1 to 8 % by weight (polymer component) based on the ink composition and increases the ink viscosity by dissolving and swelling in an alkaline area in the polar solvent containing water to associate with the particle surface of the pigment. More preferred is the water based ink composition for a ballpoint pen in which the particle surface of the pigment is subjected to surface treatment with a pigment surface-treating agent.

Best Mode for Carrying Out the Invention

The alkali-swelling associative thickener used for the ink composition of the present invention has two thickening actions. The first thickening action is the action in which the thickener is dissolved only in an alkaline area in water or a mixture of water and a polar solvent and a hydrophilic group such as a carboxylic group in the molecule is hydrated and swollen to produce a steric hindrance resistance, whereby the viscosity goes up. The second thickening action is the action in which a hydrophobic group and a hydrophilic group in the molecule are associatively adsorbed on the components in the ink, for example, a pigment, a solvent and a

surfactant to form a network-like aggregate, whereby the viscosity goes up. The first thickening action of the present thickener brought about by swelling in alkaline can provide an ink of a pseudo-plastic fluid which is reduced in a viscosity by applying shearing force. Since the shearing force is applied to the ink in writing, the viscosity of the ink is reduced and the follow-up property of the ink is improved, so that the drawn lines having no splitting can be obtained. The property of the present thickener that it is soluble only in an alkaline area results in providing the drawn lines with water resistance because of insolubility in city water and rainwater almost all of which fall in an acid area.

The second thickening action of the present thickener exerted by the associative property is brought about by allowing the pigment particles to form a network-like aggregate with the thickener. As a result the pigment itself contained in the ink is inhibited from settling over a long period of time, and seepage of the ink in the circumference of the rotary ball immediately after writing is prevented by allowing the ink to which shearing force is applied to recover soon from the reduced viscosity and to become a non-thixotropic fluid, whereby the drawn lines having no stain caused by blobbing can be obtained.

The water based ink for a ballpoint pen of the present invention which can be stored over an extended period of time has been achieved by having both of these two thickening actions, and even if the water based ink is stored in a simplified ink free type ballpoint pen such as a ballpoint pen using an oil based ink which has structure in which an ink is stored directly in a barrel to be fed to a rotary ball at a pen tip, the ink does not seep from the circumference of the rotary ball, and the writing property is good, so that the excellent drawn lines can be obtained.

The alkali-swelling associative thickener used in the present invention comprises a polymer having a carboxyl group and a hydrophobic group. The hydrophobic group includes, for example, linear and cyclic hydrocarbon groups, an aromatic hydrocarbon group, a halogenated alkyl group, an organosilicon group (SiR_3) and a fluorinated carbon group ($\text{C}_n\text{F}_{2n+1}$).

Specific examples of the polymer include polyacrylic acid, polymethacrylic acid, polyacrylic acid copolymers and polymethacrylic acid copolymers. The commercial products include "Primal TT-935", "Primal TT-950", "Primal TT-615" and "RM-825" each manufactured by Rohm & Haas Co., Ltd.

These alkali-swelling associative thickeners have a

content falling in a range of from 0.1 to 8 % by weight, preferably 0.1 to 2.0 % by weight based on the ink composition in terms of the polymer component.

"RM-4" and "RM-5" each having a few hydrophobic group manufactured by Rohm & Haas Co., Ltd., though they are the alkali-swelling associative thickeners, have little associative property and do not have the thickening actions described above.

A colorant component used for the ink composition of the present invention shall not specifically be restricted, and pigments usually used for water based inks are used. To be specific, they include inorganic pigments such as carbon black, iron oxide, titanium oxide and metal powders, organic pigments such as azos, anthraquinones, condensed polyazos, thioindigos, metal complex salts, phthalocyanines, perinone, perylenes, dioxazines and quinacridones, white pigments which are polymer particles themselves obtained by emulsion polymerization, and dyed pseudo-pigments and water based dispersions of dyed pseudo-pigments both of which are obtained by dyeing polymer particles with fluorescent dyes and dyes.

These pigments may be added either alone or in combination of two or more kinds thereof, and the content thereof falls usually in a range of from 3 to 50 % by

weight, preferably 5 to 30 % by weight based on the whole ink composition.

When a hydrophobic group and a hydrophilic group are present on the surface of these pigment particles, a network-like aggregate is formed by associative adsorption thereof with an alkali-swelling associative thickener, and the thickening effect can be promoted. The preferred particle diameter of the pigment is 500 nm or less.

When associative adsorption on a functional group on the surface of the pigment itself is small, a pigment surface-treating agent is adsorbed on the surface of the pigment, and the thickening effect can be promoted by associative adsorption of the functional groups thereof with the alkali-swelling associative thickener.

The pigment surface-treating agent includes water soluble polymers and surfactants. The water soluble polymers include polyacrylic acid resins, styrene-acrylic acid resins, styrene-maleic acid resins, polyvinyl alcohol, polyvinylpyrrolidone, polyethylene-polyethylene glycol copolymers, alginic acid and cellulose, and the surfactants include nonionic surfactants such as fatty acid esters of polyhydric alcohols, higher fatty acid esters of sugar, polyoxyalkylene higher fatty acid esters and alkylphosphoric acid esters, and anionic surfactants

such as alkylsulfonic acid salts of higher fatty acid amides and alkylarylsulfonic acid salts.

These pigment surface-treating agents each may be used alone or in combination of two or more kinds thereof, and the content thereof is preferably 0.1 to 5.0 % by weight based on the ink composition, but the range thereof shall not be restricted.

A polar solvent containing water is used for the ink composition of the present invention, and water is used as the main solvent. All solvents which are miscible with water and have polar groups can be used as the other polar solvents. There can be used, for example, ethylene glycol, diethylene glycol, triethylene glycol, polyethylene glycol, propylene glycol, dipropylene glycol, polypropylene glycol, thiodiglycol, methyl cellosolve, butyl cellosolve, methyl carbitol, ethyl carbitol, glycerin, polyglycerin, pyrrolidone and triethanolamine. They can be used alone or in combination of two or more kinds selected from them. The content thereof is 5 to 50 % by weight, preferably 10 to 30 % by weight based on the ink composition.

Other additives include as lubricants, nonionic surfactants such as fatty acid esters of polyhydric alcohols, higher fatty acid esters of sugar, polyoxyalkylene higher fatty acid esters and

alkylphosphoric acid esters, anionic surfactants such as alkylsulfonic acid salts of higher fatty acid amides and alkylarylsulfonic acid salts, which are used for the pigment surface-treating agents, derivatives of
5 polyalkylene glycols, fluorine base surfactants and polyether-modified silicones.

Rust preventives include benzotriazole, tolyltriazole, dicyclohexylammonium nitrite and saponins, and pH controlling agents include ammonia, urea,
10 triethanolamine, aminomethylpropanol and sodium hydroxide. Preservatives or fungicide include phenol, sodium omadine, sodium benzoate and benzimidazole base compounds.

A production process of the water based pigment ink composition for a ballpoint pen of the present invention
15 are composed of three steps of a dispersion step for a pigment, an ink-preparing step and a thickening step.

The pigment dispersion step comprises sufficiently dispersing a pigment, a surface treating agent, a solvent, water and additives, by means of a bead mill, a ball mill,
20 three rolls or a high-speed mixer and then centrifuging and filtering the dispersion to remove coarse particles, whereby an aqueous dispersion of the pigment is obtained.

When polymer particles obtained by emulsion polymerization are used as the pigment, they are diluted
25 to a suitable concentration and dyed with a dye. Then,

they are centrifuged and filtered, whereby the similar aqueous dispersion of the pigment can be obtained.

Attention has to be paid to the dispersion state of the pigment itself and to the kind and the content of the surface treating agent since there is the possibility that the associative thickening action changes at the subsequent thickening step. As described above, included is, for example, controlling of the pigment particle diameter to 500 nm or less.

At the ink-preparing step, the aqueous dispersion of the pigment, water and the remaining components required for the water based ink for a ballpoint pen and a controlling agent required for the alkali-swelling thickening action and the associative thickening action are blended and sufficiently stirred by means of a stirrer until a homogeneous solution is obtained.

At the thickening step, the thickener, which is dissolved and diluted with water and a polar solvent, is added to the water based pigment ink prepared at the ink-preparing step and sufficiently blended by means of a stirrer until a homogeneous solution is obtained. Finally, coarse particles are preferably removed once again by centrifugation and filtering.

The present invention shall more specifically be explained below with reference to examples, but the present invention shall not be restricted by these examples.

- 5 The ink compositions obtained in the examples and the comparative examples were tested by the following methods.

Initial particle diameter of pigment:

- 10 The average particle diameter (μm) was determined by means of NICOMP 370 (manufactured by Nozaki & Co., Ltd.) according to a photon correlation method within a week after preparing the inks.

- 15 Particle diameter of pigment after six months:

After leaving standing at room temperature for six months after preparing the inks, the particle diameter (μm) was determined by the same method as used in measuring the initial particle diameter.

20

Viscosity of the inks:

The viscosity value ($\text{mPa}\cdot\text{s}$) at 1 rpm was determined at 25°C by means of an EMD type viscometer (manufactured by Toki Sangyo Co., Ltd.).

25

Ink-seeping resistance:

The ink was filled into a refill comprising a polypropylene-made ink reservoir having an inner diameter of 3.5 mm and a length of 100 mm and having no feed and a stainless steel-made pen tip having a ball diameter of 0.5 mm. This refill was left standing at room temperature for 24 hours with the pen tip part turned downward, and then an ink-seeping state in the circumference of the ball at the pen tip part was judged with eyes according to the following criteria:

- ◎: no ink seepage in the circumference of the ball at the pen tip part
- : slight ink seepage in the circumference of the ball at the pen tip part
- △: a little ink seepage in the circumference of the ball at the pen tip part
- ×: very much ink seepage in the circumference of the ball at the pen tip part

Writing property:

The same pen as described above was prepared and used for quick writing, and the presence of starving and splitting in the resulting lines was judged with eyes according to the following criteria:

- ◎: no starving and splitting

- : slight starving and splitting
△: a little starving and splitting
×: very much starving and splitting

5 Examples 1 to 4

Pigment dispersion step:

 Sufficiently dispersed and blended by means of a
dissolver were 8.0 parts by weight of carbon black, 6.0
parts by weight of a 30 % styrene-maleic acid aqueous
10 solution as a pigment surface-treating agent, 5.0 parts
by weight of propylene glycol as a polar solvent, 30.8
parts by weight of water and 0.2 part by weight of
aminomethylpropanol as a pH controlling agent. Then, the
solution was filtered to remove coarse particles, whereby
15 an aqueous dispersion of the pigment having a pH of 9.0
was obtained.

Ink-preparing step:

 Added to the aqueous dispersion of the pigment
obtained at the step described above were 0.5 part by
20 weight of phosphoric ester as an adjusting agent, 15.0
parts by weight of propylene glycol as a polar solvent,
28.0 parts by weight (Examples 2 and 4) or 31.0 parts by
weight (Examples 1 and 3) of water, 0.1 part by weight of
aminomethylpropanol as a pH controlling agent and 0.4
25 part by weight of a rust preventive and a fungicide, and

they were sufficiently blended by means of a stirrer until a homogeneous solution was obtained, whereby a raw ink solution having a pH of 9.0 was obtained.

Thickening step:

5 A 10 % aqueous solution of an alkali-swelling associative thickener was prepared, and a prescribed amount thereof (Table 1) was added to the raw ink solution prepared at the ink-preparing step and sufficiently blended by means of a stirrer until
10 homogeneous solution was obtained. Finally, coarse particles were removed once again by filtering, whereby a water based ink composition for a ballpoint pen having an adjusted viscosity was obtained.

 Test results of these ink compositions are shown in
15 Table 1.

Examples 5 to 8

 Water based ink compositions were obtained at recipes shown in Table 2 in the same manner as Examples 1
20 to 4.

 Test results of these ink compositions are shown in Table 2.

Comparative Examples 1 to 4

25 The alkali-swelling associative thickeners were

changed to xanthane gum (Comparative Examples 1 and 2), polyacrylic acid (Comparative Example 3) and an emulsion to be thickened in alkaline (Comparative Example 4), whereby water based ink compositions were obtained at recipes shown in Table 3 in the same manner as the examples.

Test results of these ink compositions are shown in Table 3.

Components to which note numbers were put in Tables 1 to 3 are as follows:

- *1 Carbon black : MFC-88 (manufactured by Mitsubishi Chemicals Corporation)
- *2 Naphthol red : Fuji Red 2510 (manufactured by Fuji Dye Co., Ltd.)
- *3 Phosphoric acid ester : RS-610 (manufactured by Toho Chemical Industry Co., Ltd.)
- *4 Primal TT-935 (manufactured by Rohm & Haas Co., Ltd.) was diluted with water to adjust a polymer component to 10 %.
- *5 Primal TT-615 (manufactured by Rohm & Haas Co., Ltd.) was diluted with water to adjust a polymer component to 10 %.
- *6 Kelzan (manufactured by Sansho Co., Ltd.) was diluted with water to adjust a polymer component to 10 %.
- *7 Hiviswako 104 (manufactured by Wako Pure Chemical

Industries, Ltd.)

was diluted with water to adjust a polymer component
to 10 %.

*8 Primal RM-5 (manufactured by Rohm & Haas Co., Ltd.)

5 was diluted with water to adjust a polymer component
to 10 %.

Table 1

	Example			
	1	2	3	4
<u>Dispersion step</u>				
Carbon black #1	8.0	8.0	8.0	8.0
Styrene-maleic acid 30 % aqueous solution	6.0	6.0	6.0	6.0
Aminomethylpropanol	0.2	0.2	0.2	0.2
Propylene glycol	5.0	5.0	5.0	5.0
Water	30.8	30.8	30.8	30.8
<u>Ink-preparing step</u>				
Phosphoric acid ester #3	0.5	0.5	0.5	0.5
Aminomethylpropanol	0.1	0.1	0.1	0.1
Propylene glycol	15.0	15.0	15.0	15.0
Water	31.0	28.0	31.0	28.0
Rust preventive and fungicide	0.4	0.4	0.4	0.4
<u>Thickening</u>				
Associative thickener 10 % aqueous solution #4	3.0	6.0		
Associative thickener 10 % aqueous solution #5			3.0	6.0
<u>Test items</u>				
Pigment initial particle diameter (μm)	110	122	116	128
Pigment particle diameter after 6 months (μm)	112	123	115	128
Viscosity of ink ($\text{mPa}\cdot\text{s}$)	115	186	195	326
Ink-seeping resistance	○	◎	◎	◎
Writing property	◎	◎	◎	○

Table 2

	Example			
	5	6	7	8
<u>Dispersion step</u>				
Naphthol red #2	7.0	7.0	7.0	7.0
Phosphoric acid ester #3			0.5	
Styrene-maleic acid 30 % aqueous solution	6.0	6.0	6.0	6.0
Aminomethylpropanol	0.2	0.2	0.2	0.2
Propylene glycol	5.0	5.0	5.0	
Glycerin				5.0
Water	31.8	31.8	31.8	31.8
<u>Ink-preparing step</u>				
Phosphoric acid ester #3	0.5	0.5		0.5
Aminomethylpropanol	0.1	0.1	0.1	0.1
Propylene glycol	15.0	15.0	15.0	
Glycerin				15.0
Water	30.0	26.0	30.0	28.0
Rust preventive and fungicide	0.4	0.4	0.4	0.4
<u>Thickening</u>				
Associative thickener 10 % aqueous solution #4				6.0
Associative thickener 10 % aqueous solution #5	4.0	8.0	4.0	
<u>Test items</u>				
Pigment initial particle diameter (μm)	95	115	121	107
Pigment particle diameter after 6 months (μm)	97	115	120	108
Viscosity of ink (mPa·s)	218	405	383	211
Ink-seeping resistance	◎	◎	◎	○
Writing property	◎	○	○	◎

Table 3

	Comparative Example			
	1	2	3	4
<u>Dispersion step</u>				
Carbon black #1	8.0	8.0		8.0
Naphthol red #2			7.0	
Styrene-maleic acid 30 % aqueous solution	6.0	6.0	6.0	6.0
Aminomethylpropanol	0.2	0.2	0.2	0.2
Propylene glycol	5.0	5.0	5.0	5.0
Water	30.8	28.8	31.8	18.8
<u>Ink-preparing step</u>				
Phosphoric acid ester #3	0.5	0.5	0.5	0.5
Aminomethylpropanol	0.1	0.1	0.1	0.1
Propylene glycol	15.0	15.0	15.0	15.0
Water	30.0	28.0	28.0	26.0
Rust preventive and fugicide	0.4	0.4	0.4	0.4
<u>Thickening</u>				
Xanthane gum 10 % aqueous solution #6	4.0	8.0		
Polyacrylic acid 10 % aqueous solution #7			6.0	
Alkali-thickened emulsion #8				20.0
<u>Test items</u>				
Pigment initial particle diameter (μm)	121	143	117	113
Pigment particle diameter after 6 months (μm)	397	685	264	281
Viscosity of ink (mPa·s)	301	452	293	196
Ink-seeping resistance	○	◎	△	×
Writing property	△	×	△	△

The following are apparent from the results shown in Table 1 to Table 3.

The ink compositions obtained in the examples do not change in the pigment particles over an extended period of time. That is, the pigments do not coagulate to grow large, and therefore the stability can be maintained over a long period of time without causing settling. Further, if the ink composition of the present invention is filled into a pen having simplified free ink type ballpoint pen structure having no ink absorber and feed, ink seepage in the circumference of the rotary ball at the pen tip is not caused, and the written lines have little starving and splitting.

Industrial Applicability

The water based ink composition for a ballpoint pen of the present invention has a good follow-up property of the ink in writing, and the written lines are in the state that skipping, starving, splitting and stain by blobbing are not caused and the water resistance is good as well. Further, it is a water based ink composition which is stable over a long period of time without settling of the pigment itself and can be filled into a ballpoint pen of a simplified free ink type having no ink absorber and feed.

Claims

1. A water based ink composition for a ballpoint pen which comprises an alkali-swelling associative thickener comprising a polymer having a carboxyl group and a hydrophobic group, a pigment, a polar solvent containing water and a pH controlling agent.
5
2. The water based ink composition for a ballpoint pen as described in claim 1, wherein the alkali-swelling associative thickener is contained in a proportion of 0.1 to 8 % by weight (polymer component) based on the ink composition and dissolves and swells in an alkaline area in the polar solvent containing water to associate with the particle surface of the pigment, thereby increasing the ink viscosity.
10
15
3. The water based ink composition for a ballpoint pen as described in claim 2, wherein the pigment particles are subjected to surface treatment with a pigment surface-treating agent.
20
4. The water based ink composition for a ballpoint pen as described in claim 3, wherein the pigment surface-treating agent is a water soluble polymer and/or a surfactant.
25

Abstract

A water based ink composition for a ballpoint pen which is comprises an alkali-swelling associative thickener comprising a polymer having a carboxyl group and a hydrophobic group, a pigment, a polar solvent containing water, a pH controlling agent and other additives. It is a water based ink composition which is stable over a long period of time without settling of the pigment itself and can be filled into a ballpoint pen having simplified ink free type structure as is the case with a ballpoint pen using an oil based ink.

Declaration and Power of Attorney For Patent Application

特許出願宣言書及び委任状

Japanese Language Declaration

日本語宣言書

下記の氏名の発明者として、私は以下の通り宣言します。

As a below named inventor, I hereby declare that:

私の住所、私書箱、国籍は下記の私の氏名の後に記載された通りです。

My residence, post office address and citizenship are as stated next to my name.

下記の名称の発明に関して請求範囲に記載され、特許出願している発明内容について、私が最初かつ唯一の発明者（下記の氏名が一つの場合）もしくは最初かつ共同発明者であると（下記の名称が複数の場合）信じています。

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

WATER BASED INK COMPOSITION

FOR BALLPOINT PEN

上記発明の明細書（下記の欄でx印がついていない場合は、本書に添付）は、

the specification of which is attached hereto unless the following box is checked:

☒ Dec. 8, 1997
月 日に提出され、米国出願番号または特許協定条約
国際出願番号を _____ とし、PCT/JP97/04480
(該当する場合) _____ に訂正されました。

☐ was filed on _____
as United States Application Number or
PCT International Application Number
_____ and was amended on
(if applicable).

私は、特許請求範囲を含む上記訂正後の明細書を検討し、内容を理解していることをここに表明します。

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

私は、連邦規則法典第37編第1条56項に定義されるとおり、特許資格の有無について重要な情報を開示する義務があることを認めます。

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

Japanese Language Declaration
(日本語宣言書)

私は、米国法典第35編119条(a)-(d)項又は365条(b)項に基づき下記の、米 国以外の国の少なくとも一ヶ国を指定している特許協力条約365(a)項に基づく国際出願、又は外国での特許出願もしくは発明者証の出願についての外国優先権をここに主張するとともに、優先権を主張している、本出願の前に出願された特許または発明者証の外国出願を以下に、枠内をマークすることで、示しています。

Prior Foreign Application(s) Patent Appln.

外国での先行出願
Hei 8-328754

(Number)
(番号)

Japan

(Country)
(国名)

9/Dec./1996

(Day/Month/Year Filed)
(出願年月日)

Priority Not Claimed
優先権主張なし ☐

(Number)
(番号)

(Country)
(国名)

(Day/Month/Year Filed)
(出願年月日) ☐

私は、第35編米国法典119条(e)項に基づいて下記の米国特許出願規定に記載された権利をここに主張いたします。

(Application No.)
(出願番号)

(Filing Date)
(出願日)

(Application No.)
(出願番号)

(Filing Date)
(出願日)

私は、下記の米国法典第35編120条に基づいて下記の米国特許出願に記載された権利、又は米国を指定している特許協力条約365条(c)に基づき権利をここに主張します。また、本出願の各請求範囲の内容が米国法典第35編112条第1項又は特許協力条約で規定された方法で先行する米国特許出願に開示されていない限り、その先行米国出願書提出日以降で本出願書の日本国内または特許協力条約国際提出日までの期間中に入手された、連邦規則法典第37編1条56項で定義された特許資格の有無に関する重要な情報について開示義務があることを認識しています。

(Application No.)
(出願番号)

(Filing Date)
(出願日)

(Status: Patented, Pending, Abandoned)
(現況: 特許許可済、係属中、放棄済)

(Application No.)
(出願番号)

(Filing Date)
(出願日)

(Status: Patented, Pending, Abandoned)
(現況: 特許許可済、係属中、放棄済)

私は、私自身の知識に基づいて本宣言書中で私が行なう表明が真実であり、かつ私の入手した情報と私の信じることに基づき表明が全て真実であると信じていること、さらに故意になされた虚偽の表明及びそれと同等の行為は米国法典第18編第1001条に基づき、罰金または拘禁、もしくはその両方により処罰されること、そしてそのような故意による虚偽の表明を行なえば、出願した、又は既に許可された特許の有効性が失われることを認識し、よってここに上記のごとく宣誓を致します。

I hereby claim foreign priority under Title 35, United States Code, Section 119 (a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

I hereby claim the benefit under Title 35, United States Code, Section 119(e) of any United States provisional application(s) listed below.

I hereby claim the benefit under Title 35, United States Code, Section 120 of any United States application(s), or 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code Section 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of application.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Page 2 of 3

Japanese Language Declaration (日本語宣言書)

委任状: 私は下記の発明者として、本出願に関する一切の手続きを米特許商標局に対して遂行する弁護士または代理人として、下記の者を指名いたします。(弁護士、または代理人の氏名及び登録番号を明記のこと)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith (list name and registration number)

SEE ATTACHED

書類送付先

Send Correspondence to:

Martin E. Goldstein, Esq.
Darby & Darby
805 Third Avenue
New York, NY 10022

直接電話連絡先: (名前及び電話番号)

Direct Telephone Calls to: (name and telephone number)

Martin E. Goldstein
(212) 527-7697

唯一または第一発明者名

Full name of sole or first inventor

Masaru MIYAMOTO

発明者の署名

日付 April 12, 1999

Inventor's signature

Date

住所

Yokohama-shi, Kanagawa, Japan, JPX

Residence

国籍

Japan

Citizenship

私書箱

13-8-207, Idogayashimo-cho, Minami-Ku,

Post Office Address

Yokohama-shi, Kanagawa, Japan

第二共同発明者

Full name of second joint inventor, if any

第二共同発明者

日付

Second inventor's signature

Date

住所

Residence

国籍

Citizenship

私書箱

Post Office Address

(第三以降の共同発明者についても同様に記載し、署名をすること)

(Supply similar information and signature for third and subsequent joint inventors.)

Page 3 of 3

POWER OF ATTORNEY

2/

Gordon D. Coplein #19,165
William F. Dudine, Jr. #20,569
Michael J. Sweedler #19,937
S. Peter Ludwig #25,351
Paul Fields #20,298
Harold E. Wurst #22,183
Joseph B. Lerch #26,936
Melvin C. Garner #26,272
Ethan Horwitz #27,646
Beverly B. Goodwin #28,417

Adda C. Gogoris #29,714
Martin E. Goldstein #20,869
Bert J. Lewen #19,407
Henry Sternberg #22,408
Robert A. Green #28,301
Peter C. Schechter #31,662
Robert Schaffer #31,194
David R. Francescani #25,159
Robert C. Sullivan, Jr. #30,499
Ira J. Levy #35,587
Joseph R. Robinson #33,448